

SCOFIELD® Cureseal™ 700

Concrete Sealer

A solvent-based, VOC compliant, non-yellowing, curing, and sealing compound for newly poured and existing concrete surfaces.



A SIKA BRAND

■ 1. Product Description:

SCOFIELD® Cureseal™ 700 is a solvent-based, VOC compliant, non-yellowing, curing, and sealing compound for newly poured and existing concrete surfaces. The product is formulated for curing and sealing uncolored concrete, integrally colored concrete, and color hardened (shake-on) concrete, stamped or stenciled concrete, and cementitious overlays. It is recommended for use with CHROMIX® Admixtures for Color-Conditioned® Concrete integral coloring systems, LITHOCHROME® Color Hardener, LITHOCHROME® Chemstain® Classic, SCOFIELD® Texturetop® Pro Stencil Grade overlay, and SCOFIELD® Texturetop® Pro Stamp Grade overlay. It is suitable for residential or commercial projects, interior floors, exterior hardscapes, and vertical surfaces

SCOFIELD® Cureseal™ 700 visually enhances the concrete color, protects the surface from dirt and staining, and minimizes the affects of de-icing salts and exposure to gas or oil. It is well suited for application to cured concrete to prevent absorption or penetration of many fats, oils, greases, aliphatic solvents, salts, acids, and other chemicals. By preventing penetration of these compounds, SCOFIELD® Cureseal™ 700 provides good economical protection for floors and hardscapes, thereby reducing maintenance costs.

As a curing compound, it improves the surface strength, abrasion resistance, and durability of the concrete, and reduces the potential for plastic cracking. It forms a moisture barrier that prevents free lime in the concrete from migrating and reacting at the surface, forming a dust residue. Curing with SCOFIELD® Cureseal™ 700 also provides interim construction protection from most oils, greases, chemical spills, and from the adhesion of mortar splashes. Final cleanup costs are reduced and the resulting concrete surface appearance is greatly enhanced. SCOFIELD® Cureseal™ 700 can also be applied to old concrete, terrazzo, brick, and masonry tiles to dust proof and impart stain and chemical resistance.

SCOFIELD® Cureseal™ 700 is a Methyl Methacrylate Acrylic copolymer specifically designed to meet the moisture retention properties of AASHTO M 148, ASTM C309, and ASTM C1315, when applied at the recommended coverage rate. It is a clear liquid (25% solids by weight), which dries to a high gloss, breathable, UV resistant film. SCOFIELD® Cureseal™ 700 complies with all VOC (<700 g/L) requirements and other Federal and State Air Quality Regulations. Be sure to check the VOC requirements in your area prior to use. The longevity of SCOFIELD® Cureseal™ 700 depends upon the dried film thickness, exposure, and use conditions. Clear sealers will scratch and scuff, and will require maintenance. Treated surfaces are readily recoated with adequate cleaning.

■ 2. Limitations:

Do not use on concrete slabs with inadequately drained sub-grade and/or surfaces subject to hydrostatic water pressures. Do not use in swimming pools, fountains or ponds. Do not use on surfaces that will have direct food contact. Do not use for recoating or in conjunction with other floor sealers, treatments, bond breakers, or adhesives without prior test to determine compatibility and adhesion. Do not use to fill or repair cracks in the substrate.

Warning: Treated surfaces may be slippery during application prior to drying, and when wet with water or liquids after drying. Concrete should be textured sufficiently to eliminate potential slipping hazards. In addition, use SCOFIELD® Traction Additive with the SCOFIELD® Cureseal™ 700. Interior floors may be maintained with a slip resistant wax. Test and confirm that the treated surface is adequately slip resistant prior to opening installation to any traffic.

■ 3. Chemical Resistance:

SCOFIELD® Cureseal™ 700 provides 24-hour spot resistance to the following chemicals with little, if any, coating effect:

<i>antifreeze</i>	<i>deicing salts</i>
<i>foods</i>	<i>fruit juices</i>
<i>vegetable oil</i>	<i>vegetable extracts</i>
<i>diesel fuel</i>	<i>petroleum oil</i>
<i>ethanol</i>	<i>power steering fluid</i>
<i>calcium chloride</i>	<i>sodium chloride</i>

For materials not appearing in this chart, a test application is necessary.

■ 4. Packaging:

Container	Content
Pail	5 US gallon (19.0 L)

■ 4.1. Shelf Life:

Indefinite, when stored in original, unopened containers, in dry storage.

■ 5. Coverage:

Coverage rates vary with surface texture and porosity, ambient and surface temperatures and method of application. The following coverage rates are approximate for broom finish concrete surfaces:

Curing:	300ft ² /gal (7.4 m ² /L)
Sealing:	300-400 ft ² /gal (7.4-9.8 m ² /L)

Avoid excessive build-up, particularly in the depressed textures and grout joints of stamped or stenciled concrete, hand tooled or saw cut joints. Thicker applications may lead to discoloration and diminished sealer performance. Wipe up or brush out excessive material before the film becomes tacky.

■ 6. Application:

SCOFIELD® Cureseal™ 700 may be applied using a roller, hand pump sprayer, or airless sprayer. If using a roller, a non-shed solvent resistant roller with 1/4"-1/2" nap length is recommended. The nap length of the roller will depend on the surface porosity and texture of the concrete. Best results are obtained when product is applied at substrate temperatures in excess of (50° F), (10° C). Do not apply at or below (50° F) (10° C) or when such temperatures are expected within 72 hours following application. Control interior environment to prevent condensation from forming on the surface prior to sealing and before the sealer has become tack free. Do not apply if there are concerns with the quality of the color or finish of



the concrete, until those concerns are adequately addressed.

When using a sprayer, apply material with a fan pattern nozzle. Spray equipment should be clean and in good working condition. Sprayer seals must be solvent resistant. Hand pump sprayers must be capable of delivering moderately viscous liquids. Care must be taken to protect adjacent areas from over spray.

■ 6.1. NEW CONCRETE: UNCOLORED, INTEGRALLY COLORED, COLOR HARDENED:

Apply SCOFIELD® Cureseal™ 700 immediately following final finishing and after the slab is firm enough to walk on without damage. Do not apply if bleed water is present. Apply to vertical surfaces immediately following form removal. Avoid runs or puddles and over application. To achieve maximum sealing and dust-proofing benefits, a second application should be made at least two weeks after the cure coat application. Surfaces to be retreated should be dry and clean. Apply in a continuous wet surface film. Application of product over excessively smooth, hard-troweled surfaces may result in adhesion loss.

■ 6.2. COLORED STAMPED OR STENCILED CONCRETE:

After concrete has been stamped using LITHOCHROME® Antiquing Release, thoroughly remove the residual release powder by washing and scrubbing. The concrete should be allowed to dry thoroughly before applying SCOFIELD® Cureseal™ 700. If SCOFIELD® Liquid Release BG is used, do not apply SCOFIELD® Cureseal™ 700 until the liquid release has sufficiently evaporated (no wet sheen gloss) from the surface. Read the LITHOCHROME® Antiquing Release and the SCOFIELD® Liquid Release BG Technical Data Sheets before applying products. All information is available for download online at www.scofield.com or at 800-800-9900.

■ 6.3. EXISTING CONCRETE:

Adequately remove accumulations of grease, oil residue, incompatible curing, or sealing compound residue and other substances that would diminish adhesion. Wash surfaces thoroughly. Allow surface and joints to adequately dry before applying SCOFIELD® Cureseal™ 700. Very rough, porous and deeply textured surfaces may require multiple applications to ensure the formation of a protective film, without pinholes or holidays.

Before application of sealer the Moisture Vapor Emission Rate (MVER) of the concrete or cementitious topping must be measured and be less than 5 pounds per 1000 square feet per 24 hours (2.27 kg/92.9 m² per 24 hours). Promptly clean application equipment with Xylene following use. Handle and dispose of cleaning residue properly.

■ 7. Maintenance:

Periodically inspect cured and sealed surfaces for wear or damage. All concrete curing and sealing compounds will eventually exhibit the affects of weathering and traffic. For maximum coating life and performance, wipe up all chemical solvent or petroleum spills as soon as possible. Remove abrasive debris by sweeping or vacuuming. Do not drag, drop or place sharp edges on sealed surfaces. Periodic washings with mild detergents will help maintain surface luster. Do not use solvent or acid based cleaning materials for general cleaning. Hot car tires or turning tires while car is standing may damage the sealer. Surfaces that will be subjected to car traffic, de-icing salts or chemical exposure, must receive minimally, two applications of SCOFIELD® Cureseal™ 700.

Prior to recoating, the surface and joints must be clean, dry, free from cleaning product residue, other contamination, or loose materials, which will affect the adhesion of SCOFIELD® Cureseal™ 700. When recoating, SCOFIELD® Traction Additive must be added to the sealer.

■ 7.1. INTERIOR FLOORS:

Regularly clean by dry and wet mopping. Periodically machine scrub, rinse, and wet vacuum the surface. Apply a maintenance wax or slip resistant wax as directed by the wax manufacturer. This type of periodic maintenance will greatly enhance the appearance of the floor and minimize the need to strip and/or reapply the sealer.

■ 7.2. DRY TIME:

Drying times will vary depending upon wet film thickness, surface texture and porosity, ambient and surface temperatures, humidity, and if the product is being used as a cure coat or a seal coat. At 70° F, approximate dry times:

Tack free: 1 hour
Light foot traffic: 6 hours
Light car traffic: 24 hours
Normal car traffic: 72 hours

■ 8. Quality Control:

Cast a job site sample at least 21 days prior to the installation for approval of color and finish. Utilize all materials, tools, and techniques from the actual job in the mock-up. Consistent batching, pouring, finishing, curing, sealing, and preparation techniques, will ensure the uniformity of architectural concrete. Verify adequate wet and dry slip resistance. Discuss maintenance requirements. Site visits by Scofield personnel are for making technical recommendations only and not for supervising or providing quality control. Maintenance requirements should also be discussed.

■ WARNING

Combustible liquid and vapor. Extinguish all pilot lights and other sources of open flame. May cause eye, skin, and respiratory irritation. Do not take internally. Keep out of reach of children and animals. Wear an organic respirator, eye protection, and protective clothing during application. Cover plant material. Ensure adequate ventilation during and after application. Prevent fumes from entering the HVAC system. In case of spillage, absorb and dispose of material in accordance with local, state, and federal regulations. Before use, read the Safety Data Sheet (SDS). All information is available for download online at www.cofield.com or at 800-282-3388.

■ WARRANTY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at <http://usa.sika.com/> or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452.



Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.



A SIKA BRAND

■ Scofield customer service: 1 800 800 9900
4155 Scofield Road, Douglasville, GA 30134 voice: 770 920 6000 fax: 770 920 6060

www.scofield.com