

PRODUCT DATA SHEET

CHROMIX® Admixtures for Color-Conditioned® Concrete

PRE-PACKAGED INTEGRAL COLORING ADMIXTURE FOR DECORATIVE ARCHITECTURAL CONCRETE PLACEMENTS AND PRECAST STRUCTURES.

PRODUCT DESCRIPTION

CHROMIX® Admixtures for Color-Conditioned® Concrete are pre-packaged, easy to disperse bags of integral coloring admixture that permanently color decorative architectural concrete placements, precast structures, and other cementitious materials.

With additives carefully blended into the composition, CHROMIX® Admixtures for Color-Conditioned® Concrete are designed to have minimum impact on concrete plastic properties and compensate for the increased water demand ordinary pigments have on most mix designs. Unless noted, each bag is designed to color 1 yard of concrete, and may be added directly into a concrete mix. The pulpable toss-in bag quickly disintegrates into the cement containing mix.

USES

CHROMIX® Admixtures for Color-Conditioned® Concrete can be used to color cast-in-place, precast, and dry-cast concrete floor slabs, walls, steps, sidewalks, curbs, columns, arches, blocks, pavers, and other decorative objects.

CHARACTERISTICS / ADVANTAGES

CHROMIX® Admixtures for Color-Conditioned® Concrete adds color that is weather resistant, UV Stable, lightfast, and alkali resistant. It contains no materials that initiate, accelerate, or promote the corrosion of steel, coated metal, plastic, or rubber concrete reinforcements. CHROMIX® Admixtures for Color-Conditioned® Concrete will not migrate from standing water, and can safely color concrete fountains, pools, water features, or concrete that will be polished and encounter damp or wet environments.

Single per yard toss-in dry packaging is ideal for placements in extreme weather environments, remote locations where long-term staging is required, or where complicated metering equipment is impractical.

APPROVALS / STANDARDS

All pigments used conform to the requirements of *ASTM C 979 Pigments for Integrally Colored Concrete*.

PRODUCT INFORMATION

Chemical Base	Synthetic iron oxide pigments.
Packaging	Premeasured pulpable paper bags designed to color 1 yard of a 5 or 6 cement sack mix. (470lbs/213kg or 564 Pounds/256 kg). Unit weight will vary between 15 and 50 pounds. Custom sizes available with minimum orders.

Appearance / Color	All colors depicted on Scofield's Color Chart A-312. Over 3,000 custom colors available with order minimums.
Shelf Life	24 months from the date of manufacture.
Storage Conditions	Keep dry, moisture free, and below 175 °F (80 °C).

TECHNICAL INFORMATION

Concreting Guidance	CHROMIX® Admixtures for Color-Conditioned® Concrete is designed to have minimal effect on concrete plastic and hardened properties, and to minimally interact with other concrete admixtures. As all chemical admixture interactions cannot be predicted, always test final mix designs with actual materials to be used, and perform a jobsite test sections as described later in this bulletin.
----------------------------	--

APPLICATION INFORMATION

Recommended Dosage	Color selection will determine the mix of ingredients placed into the toss-in bag. Color saturation, and intensity will determine the amount required. Typical dosages range between 0.2 to 10.0 pounds material per 94 pound sack of cement. If supplementary cementitious materials such as fly ash or blast-furnace slag are used in the mix, their weight must be added to the weight of the cement when determining the correct dosage.
Mixing	<p>Preferred Use Procedures</p> <p>Toss-in bags can be introduced at any point in the concrete mixing process, as long as enough mixing and time is given for the color to reach an unchanging uniform appearance. Typically, this will take at least 5 minutes and 130 drum revolutions at mixing speed. Automated delivery systems can be set to introduce bags early in the batching process to minimize dusting. Care must be taken to not allow disintegrating bags or product to become hung up on mixing vanes or collect in spaces where the mix has limited motion.</p>
Restrictions	Do not use with chloride based accelerators.

APPLICATION INSTRUCTIONS

Factors Influencing Final Color & Appearance

Colors represented on the CHROMIX Color Chart A-312 depict samples of broom finished concrete made with medium gray cement and cured with LITHOCHROME® Colorwax™. The final color and appearance obtained on the jobsite will be influenced by concrete composition, surface finishing technique, and curing compound/sealer selection.

Concrete composition variations that can impact color include cement type and color, aggregate selection, and the use of pozzolans such as slag or fly ash. Differences in sealer or curing compound type, such as water or solvent based, or if no sealer is used, can also influence final appearance.

Finishing techniques will influence final concrete appearance. Different tools such as wood floats, magnesium trowels, hard steel trowels, brooms, and edging tools, will each influence color, surface texture, sealer penetration, and final cured concrete appearance differently. Do not change tool types once work has begun.

Changes in water content and water-to-cement ratio, both in the mix and on the concrete surface during finishing, can influence the final surface color. Mix designs that develop excessive bleed water can float non-uniform cement/pigment ratios, and cause uneven or weak coloring. Once mix designs are established, do not add water to alter concrete plastic properties. Do not add water to loosen partially cured loads. Do not use "watering" sprinklers as colored concrete cures, or use wet brooms and tools while finishing. Any of these will likely result in inconsistent concrete color.

Placement and Finishing Tips

As freshly placed concrete cures, its color will vary with differences in surface moisture. Concrete curing in shaded areas or in the center of large slabs will surface dry slower than those exposed to sunlight or closer to form edges. This can cause color variations that will often fade with time. Avoid high salt aggregates that can cause efflorescence that can make color irregular. These visual differences can be long lasting, and raise questions about the quality of the concrete placement. Use LITHOCHROME Colorwax or COLORCURE® Concrete Sealer tinted to match the final color of the cured concrete to avoid these problems and deliver jobs that are uni-

form in color and appearance. Always evaluate composition and finishing techniques as described below.

Placements to be Ground and Polished

Use 1 bottle of SCOFIELD® Ready-Mix Truck Defoamer per concrete truckload to minimize bug holes and air voids.

Reinforcing Fiber Interactions.

If high air content is experienced with competitor reinforcing fibers, pre-wet the fibers by tumbling in the mixer three minutes with water, colorant, and 1 bottle of SCOFIELD® Ready-Mix Truck Defoamer per truckload before batching concrete into the mixer.

Jobsite Test Sections

Prior to large scale production, the concrete or cementitious mix design for each color to be produced must be made. Conduct small scale testing to demonstrate concrete from the mix design meets all slump, flow, air content, compressive strength, and any other required concrete specifications.

Prior to general jobsite use, representative Jobsite Test Section(s) or "Mock-Ups" must be produced and approved for each individual concrete color mix design, surface finish/texture, and for each curing compound/sealer combination that will be created.

Use Jobsite Test Sections to verify entire system suitability including frame/mold and foundation preparation methods, surface concrete specification compliance, finishing techniques, safety procedures, and achieved performance of the fresh and fully cured concrete. When applicable, test completed systems for wet and dry slip resistance. Evaluate polishing or coating application techniques, final color, and visual appearance. Do not proceed with products, techniques, or finishing systems that do not meet required specifications or meet with site owner approval.

Selected Jobsite Test Sections should be in close proximity to the larger job area, and made from the same concrete mix design that will be used on the larger project. Test sections should be sized to be representative of the finished project, and be produced by the same workers who will perform the project installation.

AVAILABILITY/WARRANTY

Availability

Scofield offers a complete line of engineered systems for coloring, texturing, and improving performance of architectural concrete. These include coloring admixtures, color hardeners, colored cementitious toppings, stains, curing compounds, sealers, coatings, repair products and texturing tools. Visit the Scofield website at www.scofield.com for further information.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LOCAL RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

VOC = 0 g/l

LEGAL DISCLAIMER

KEEP CONTAINER TIGHTLY CLOSED •KEEP OUT OF REACH OF CHILDREN •NOT FOR INTERNAL CONSUMPTION •FOR INDUSTRIAL USE ONLY •FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT**

IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
CHROMIX® Admixtures for Color-Conditioned® Concrete
October 2018, Version 02.01
021405071000000067

CHROMIXAdmixturesforColor-ConditionedConcrete-en-US-(10-2018)-2-1.pdf

