



PRODUCT DATA SHEET

SCOFIELD® Cure Seal 700

SCOFIELD® CURESEAL 700 IS A HIGH SOLIDS (25 %), STYRENE-ACRYLIC COPOLYMER SOLUTION FORMULATED TO ACHIEVE BOTH A PROTECTIVE AND DECORATIVE FINISH AS WELL AS ALLOW THE CONCRETE TO ATTAIN FULL MIX DESIGN PROPERTIES

PRODUCT DESCRIPTION

SCOFIELD® Cure Seal 700 is a high solids (25 %), styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. SCOFIELD® Cure Seal 700 is a film-forming sealer, which will assist the curing of freshly placed concrete. SCOFIELD® Cure Seal 700 complies with VOC regulations of <700g/L.

USES

Apply over fresh concrete for curing the concrete, or over existing concrete to seal and protect.

CHARACTERISTICS / ADVANTAGES

- High Gloss
- Wet Look
- High Solids
- UV Resistant

PRODUCT INFORMATION

Packaging	1-gallon (3.8L) cans or 5-gallon (18.9L) pails.
Shelf Life	1 year unopened, if opened use right away.
Storage Conditions	Store in a well ventilated area, away from heat sources.

APPLICATION INFORMATION

Coverage	Two thin coats are recommended for net coverage of: Smooth Troweled: 300 ft ² per gallon Textured or Stamped: 200 ft ² per gallon Uncured Broom Swept: 200 ft ² per gallon Exposed Aggregate and Pavers: 100 ft ² per gallon
-----------------	--

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

If applied over fresh concrete as a cure and seal spray with a solvent resistant sprayer, a roller may also be used if concrete is hard enough to walk on without marring the surface. For existing concrete protection clean dirt, wax, grease, oil and other contaminants from the surface, using a pressure washer, bristle brush or rotary brush. Be sure to remove any foreign coating with a chemical stripper or abrasive wheel unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with a quality cleaner degreaser. Use a bristle brush for heavily oiled spots. If surface is slick, etch with quality concrete etching product. Rinse well with a pressure washer. Allow 24 hours to dry. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand. DO NOT THIN.

APPLICATION

When applying to fresh concrete, apply evenly at the recommended rate with a solvent resistant sprayer, a roller may also be used if concrete is hard enough to walk on without marring the surface. For existing concrete, apply evenly from can or other metal container with appropriate roller. Use a long nap roller for exposed aggregate, a medium nap roller for textured surfaces and a short nap roller for smooth surfaces. Do not pour directly from can to concrete. Wait until the surface is tack-free before applying a second coat. Apply perpendicular to the first coat. Cross-rolling allows for an even application. If spraying, use a solvent resistant sprayer holding tip no more than 8" from surface during application. Back rolling is recommended while spraying. Clean up immediately with A-1 SOLVENT, Xylene or Acetone. Foot traffic should be avoided for 4 hours. Brush may be used where roller won't reach. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the dry time.

Removal

If removal is needed, use a quality chemical paint stripper.

CLEANING OF TOOLS

Clean tools with A-1 SOLVENT, Acetone or Xylene.

MAINTENANCE

Clean sealed surface with water only. Reseal surface as needed but no more than every two years to prevent buildup of sealer.

Meets or Exceeds: ASTM C-309, Type I Class A and B; ASTM C-1315-11; AASHTO Spec M-148; EPA 40 CFR Part D.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LOCAL RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

KEEP CONTAINER TIGHTLY CLOSED •KEEP OUT OF REACH OF CHILDREN •NOT FOR INTERNAL CONSUMPTION •FOR INDUSTRIAL USE ONLY •FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at

<https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
SCOFIELD® Cure Seal 700
October 2018, Version 01.01
020815110020000033

SCOFIELDCureSeal700-en-US-(10-2018)-1-1.pdf

