

NEW! SCOFIELD® REVIVE™ COLOR REFRESHER

SCOFIELD® Revive™ Color Refresher was developed to improve the appearance of existing, unsealed exterior colored or uncolored concrete surfaces in need of refurbishment or renovation. It adds a measured amount of color to the concrete without producing a paint-like appearance. Since SCOFIELD Revive Color Refresher penetrates and reacts with the concrete and no film is formed, Color Refresher becomes part of the surface. The resulting look approximates the appearance of newly placed concrete.

Colors:

- SCOFIELD Revive Color Refresher is available in a wide range of colors, including many to approximate popular colors depicted on Scofield's Color Chart A-312 CHROMIX® Admixtures for Color-Conditioned® Concrete and selections from LITHOCHROME® Color Hardener Chart A-132. It is also available in Black and in A-11 Concrete Gray that approximates the color of uncolored concrete made with medium-gray cement.
- Make to Order and colors are available with a 50-gallon minimum quantity. Custom color matching is also available; check with your Scofield rep for conditions and pricing.

Packaging:

- Base material (Part B) is available in 4-gallon pails.
- Tint concentrate (Part A) sold separately in 1-gallon cans.

Coverage:

- Typically 100-300 ft²/ gal. depending on the porosity of the concrete.
- SCOFIELD Revive Color Refresher must be applied full strength without thinning.

Ideal Uses:

- Revitalize faded, worn color
- Impart a consistent appearance to mismatched colors
- Add color to uncolored concrete or concrete pavers

Application:

- Apply with an acetone-resistant sprayer.
- May also be applied with a roller with the appropriate nap; in most circumstances a 3/4 inch nap will give the best results.

Keys to success:

- Properly prepare surfaces; remove all existing sealers and cures with LITHOCHROME™ Coating Remover, then pressure wash with a minimum of 2000 psi.
- One coat generally provides a natural look. The coverage rate will depend on the porosity of the concrete.

renovation



**SCOFIELD®
SYSTEMS**



NEW! SCOFIELD® REVIVE™ COLOR REFRESHER

renovation

Ideal for companies both large and small who want to bring faded concrete color back up to that "new" look, or bring consistency to mismatched color.

SCOFIELD Revive Color Refresher is available in the following stocked colors.

CHROMIX® Admixtures for Color-Conditioned® Concrete:

- | | | | |
|--------------------------|--------------------------|----------------------------|----------------------------|
| C-12 Mesa Beige | C-31 Shadow Slate | C-25 Sombrero Buff | 0288 Autumn Beige |
| C-20 Limestone | C-34 Dark Gray | C-27 Westwood Brown | 3987 Porcelain Gray |
| C-24 Charcoal | C-14 French Gray | C-32 Quarry Red | |
| C-26 Antique Cork | C-21 Adobe Tan | 1266 Cool Gray | |


LITHOCHROME® Color Hardener:

- | | |
|-------------------------|---------------------------|
| A-26 Brick Red | A-51 Steadman Buff |
| A-55 Pecan Tan | A-57 Platinum Gray |
| A-59 Beige Cream | 5183 Stone Gray |

Other Colors:

- | |
|---------------------------|
| A-11 Concrete Gray |
| 0510 Black |

For availability and pricing of colors not listed above, contact your Scofield representative.



SCOFIELD Revive Color Refresher can be sprayed or rolled onto the surface. Use a soft-bristled push broom to work the material into the surface until surface is dry. After 24 hours, treated surfaces might have a slight residue remaining on the surface. A quick rinse with water can remove it.



The two upper panels show untreated colored broom finished concrete, the two lower panels show the same colored panels treated with SCOFIELD Revive Color Refresher.

© L. M. Scofield Company 2010 – All rights reserved.
CHROMIX, LITHOCHROME, SCOFIELD, Color-Conditioned, and Revive are trademarks of L. M. Scofield Company.
CS 0410 REF

Prior to beginning job, consult Scofield Tech-Data Bulletin B-644.

